

Sub D6
cont.
et

~~% w/w of at least one linking compound which is miscible with said polymerizable acrylic monomer and which is capable of bonding to the surface of the oxide compound.~~

Sub D7

~~11. (Amended) Process of manufacturing an uncoated abrasion resistant polymer product comprising polymerizing and shaping an acrylic composition comprising at least 70 % w/w of the residues of at least one polymerizable acrylic monomer, 0.3 – 5 % w/w of a finely divided compound comprising at least one oxide selected from silicon, titanium, zirconium and aluminum oxides, and 0.2-25 % w/w of at least one linking compound which is miscible with said polymerizable acrylic monomer and which is capable of bonding to the surface of the oxide compound.~~

12. (Amended) Process of manufacturing an uncoated abrasion resistant polymer product comprising polymerizing and shaping a polymerizable composition comprising at least 70 % w/w of at least one polymerizable acrylic monomer, 0.2 – 5 % w/w of a finely divided compound comprising at least one oxide selected from silicon, titanium, zirconium and aluminum oxides, and 0.2-25 % w/w of at least one linking compound which is miscible with said polymerizable acrylic monomer and which is capable of bonding to the surface of the oxide compound.

See the attached Appendix for the changes made to effect the above claim(s).